



AIRCOLOR ACRYLIC PAINT

H43

VERSION: 201116
Page:1/2

ACRYLIC PAINT

DEFINITION

AIRCOLOR ACRYLIC PAINT is a premium acrylic enamel especially formulated for the quick coating of Industrial surfaces. Thanks to the atomization it can also be used on larger surfaces. An extreme high content of pigments and specific additives provide excellent opacity, high film-thickness, low tendency for runs and good adhesion direct on steel, galvanised, aluminium. It can be applied either for spot repairs or refinishing parts.

CARACTERÍSTICAS FÍSICAS

Nature:	Thermoplastic acrylic resin
Propellant:	DME
Colour:	Black, White
Specific weight:	0,8 kg/l a 20°C
Gloss (60°C):	Glossy - 70 GU a 60° Satin - 30 GU a 60° Matt - 10 GU a 60°
Aerosol pressure:	4-4,5 bar a 20°C
Yield:	2,5 m ² /spray
Dry film thickness:	15-20 µ/coat
Resistance of the container to heat:	< 50 °C
Resistance of paint to heat:	120°C
VOC:	692 g/l

Application 2004/42/EC - IIB (e)(840)

SURFACE PREPARATION

PROCESS		Paint OEM	PROCESS		Primer
	P320		√		
	DA93	√		DA93	√

APPLICATION

2'	20-25 cm	2-3 coats	5'

DRYING TIMES

20°C	10'-15'	30'	1h	15' (*)

(*) In order to increase the degree of gloss and to enhance the fuel resistance recoat with acrylic lacquer after approx 15 min. flash-off time (20°C) with 1K Clear.

REMARKS

Shake the aerosol before use for 2 minutes after hearing the sound of steel mixing balls.
Carry out test spray. Check the colour.
Drying time depends on temperature, humidity and film thickness which has been applied.

EQUIPMENT CLEANING



SAFETY

Follow instructions on the product label. For more information check the Safety Data Sheet.
Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

SHELF LIFE

One year in unopened original packaging.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO S.A.U reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

*All clauses contained herein apply to any future changes or modifications.
For any additional technical information please consult with our Customer Service or our Technical Department.*