

# Gold Plus Bodyfiller Putty TDS



v.03-02-2020

## CHARACTERISTICS:

Easy to use light filling putty characterized by good shaping properties in any required thickness. Suitable for vertical or horizontal large repair works but also for filling small imperfections. Creates smooth coat with optimum hardness. It was designed for use on steel, aluminium, galvanized surfaces and GRP.

## APPLICATION:

The surface must be cleaned, dry, degreased and matted. Thoroughly mix putty with BPO hardener. Apply within 4 - 6 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

**NOTE:** Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15° C.

## TECHNICAL DATA:

VOC 2004/42/IIIB(b)(250) max. 250 g/l

Shelf life: 12 months

Density (20°C): 1.06 – 1.12 g/cm<sup>3</sup>

Colour: beige

	Cleaning		
	Hardener addition	Putty	100 g
		BPO Hardener	2 - 3 g
	Body filling	4 - 6 min	
	Drying time	20 - 25 min	
	Hand sanding/dry	P100 - P320	
	Machine sanding/dry	P100 - P320	
	Store in cold place		



Le'Mix Pty Ltd

29 Claremont Ave Greenacre NSW 2190 Australia

lemix.com.au - info@lemix.com.au - +61297084959