

1K CLEAR COAT

TECHNICAL DATA SHEET



DESCRIPTIONS

Le'Mix 1K clear coat is a UV-resistant, fast-drying clear coat that can be applied universally at all existing base coats (solvent-based). High Gloss, good flow and good for the conservation and sealing of wood, wood composites, iron and steel for indoor and outdoor application

QUALITY AND PROPERTIES

- Fast drying time
- Easy application
- Can be used on all solvent-based paints
- UV resistant
- Good flow
- No yellowing
- For indoor and outdoor application

PHYSICAL AND CHEMICAL DATA

- Basis of binder: Acrylic resin
- Colour: transparent
- Smell: solvent
- Degree of gloss: at measurement angle 60° acc. glossy: 85 - 90 GE
- Efficiency: approx. 1,5 - 2,0 m²
- Substrate: Solvent-based basecoats,
- Drying (at 20°C, 50% relative air humidity):
- Dust-dry: after 10 minutes
- Touch-dry: after 2 hours
- Cured after 24 hours
- Temperature resistance: glossy to 110°C
- Storage stability: 10 years if appropriate storage
- Size: Aerosol cans, olume 400 ml
- VOC-Value: glossy 276,4 g


USE INSTRUCTIONS

Solvent-based paints can be top-coated with 1 component clear coat once they have dried for 30 minutes
Shake can for 2 minutes, carry out spray test,


Apply 1 medium coat, allow 5 minutes for flash off and apply 2nd coat, For an optimal coating result bring can to temperature prior to use (20 - 25 °C) and a relative air humidity of 45 - 60%




2 min



approx. 15 cm



20°C= 5 min



5 sec

Environmentally compatible: Le'Mix Pty Ltd is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal: Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse"

DISCLAIMER OF LIABILITY

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. Le'Mix Pty Ltd is not responsible for any misuse or mishandeling and therefore will not except any liability.