

WHEEL SILVER

TECHNICAL DATA SHEET



DESCRIPTIONS

Le'Mix Wheel silver paint gives a decorative shine to rims. Durable, high-pigmented protective coating for steel and alloy rims. For additional protection of the metal pigments and for higher gloss we recommend to topcoat with Le'Mix 1K clear topcoat.

PHYSICAL AND CHEMICAL DATA

Basis of the binder: acryl resin
Colour: silver
Smell: solvent
Degree of gloss (at measurement angle 60° acc. to DIN 67530)
Efficiency: Depending on consistence and color.
Drying time (at 20°C, 50% relative air humidity):
Dust-dry: after approx. 5-10 minutes
Tack-free: after approx. 10-20 minutes
Cured: after 24 hours
Coatable with clear lacquer: after approx. 2 hours.
Temperature-resistant: up to 110°C
Storage stability: upto 10 years in apropiert environment.
Size: 400 ml

QUALITY AND PROPERTIES

High-grade, quick-drying nitro-combi lacquer
Good flow, smooth surface
Weather-resistant, light-proof and non-yellowing
Limited fuel-resistant
Good colour and gloss retention
Hard surface, abrasion-resistant.

USE INSTRUCTIONS

The surface has to be clean, dry and free from rust and fat. Before use, shake the can vigorously for 2 minutes. Test spray to check colour-matching. Spray several thin coats in 3 - 5 minute intervals from a distance of approx. 25 cm. After 60 minutes drying time, coat with Le'Mix 1K topcoat clear to protect the metal pigments in the lacquer. Do not spray over synthetic paints
Carry out test spray

Environmentally compatible: Le'Mix Pty Ltd is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal: Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse"

DISCLAIMER OF LIABILITY

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. Le'Mix Pty Ltd is not responsible for any misuse or mishandeling and threrfore will not except any liability.