



LS116 (29116) SYNTOLACK



1000 ml +
150-250 ml



17-18" FC 4
at 20° C



Ø 1,4 mm
4 Atm
HVLP:
Ø 1,3 mm
2-2,5 Atm
N° of coats: 2



Air drying at 20° C
Handling: 2-3 h
Through-dry: 5-6 days

DESCRIPTION

Fast drying synthetic enamel.

USE

Suitable for refinishing commercial truck boxes and chassis, agricultural and industrial machines as well as machine tools and general ferrous substrates.

CHARACTERISTICS

- Fast drying
- Easy to apply
- Excellent gloss and flow
- Good weather resistance
- Good adhesion directly to steel (it does not contain any anticorrosive pigments; protection due to barrier-effect).

SUBSTRATE PREPARATION

It can be applied to:

- 1K FAST PRIMER
- SYNTOPRIMER
- SYNTOPRIMER ZINC
- EPOPRIMER 1K
- Directly to rust-free steel sheet suitably degreased with 00695 SILICONE REMOVER SLOW.

APPLICATION

Spray.

Mixing ratio by spray:

	weight and volume
LS116 SYNTOLACK (derived from binder 29116)	1000 parts
00824 (Slow)-00825 (Standard) LECHSYS UNIVERSAL THINNER or	150 - 250 parts
00552 LECHLEROID THINNER L or	
00572 SYNTEX THINNER SS	

Spray viscosity at 20 °C: 17- 18" FORD Cup 4

Ø Air cap: 1.4 mm; HVLP: 1.3 mm

Air pressure: 4 Atm; HVLP: 2 - 2.5 Atm

Number of coats: 2 (Flash-off between coats NOT over 2 hours at 20°C to avoid lifting and wrinkling).

Overcoatable at 20°C: up to 2 hours or after 48-72 hours according to the film thickness

Film thickness: 40-50 µ

Theoretical coverage: 1 l mixture = 6.5-7 m² at 50 µ

1 kg mixture = 6.5-7 m² at 50 µ

V.O.C. (on average) of the product ready for use: ~ 580 g/l

Mixing ratio by electrostatic spraying:

Add 0,5-2% of 09826 ADDITIVO ANTISTATICO to the product

DRYING TIME

Air drying at 20 °C

Dust-free: 20-30 min.

Handling: 2-3 h

Through-drying: 5-6 days

NOTES

It is recommended to add 1% of the specific drier 29297 LECHSYS SICCATIVE R to LS116 (29116) SYNTOLACK.

To improve the weather resistance, to accelerate the drying, to improve the direct adhesion to steel sheet and hardness after 24 hours, add 10% (weight or volume) of 29344 LECHSYS ISOLACK HARDENER, immediately prior to using.

The mixture must be used within 4-6 hours at 20°C

MATT & GLOSS TABLE

The enamels of the Syntolack family are available in different gloss levels:

MATT 3/7 GLOSS	SEMI MATT 7/15 GLOSS	SATIN MATT 15/25 GLOSS	SEMI GLOSS 30/45 GLOSS	GLOSS 50/75 GLOSS	HIGH GLOSS ≥80 GLOSS
LS112		LS400	LS401		LS116

TECHNICAL DATA SHEET N° 0361-GB
UPDATED 10/2019

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.